TECHNICAL INFORMATION

Physical properties

Total Weight: 460g/m (nominal)
Vinyl Weight: 400g/m (nominal)
Substrate Type: Osnaburg
Substrate Weight: 60g/m (nominal)

Type II and other specifications available

Tensile Strength: MD 80 N/cm (nominal)

TD 60 N/cm (nominal)

Tear Strength: 8500mN/5cm (nominal)

Roll size:

130cm x 30m - cut lengths available

Pattern Repeat

Vertical repeat every 17.5cm . Drop free

Fire Rating:

Class B when bonded To a suitable substrate (Class A2 – s1,d0 or better) Class A ASTME-84 tunnel test

Adhesive:

Newmor Heavy.

Varies with substrate - please enquire.

Bacteria Resistance:

Contains an active Fungicide.

Light Fast:

Excellent Light Fastness BS EN ISO 105-B02 7/8

Light reflective value (LRV)

Availability on request.

In architecture, light reflectance value, is a measure of visible and usable light that is reflected from a surface when illuminated by a light source.

Specifications

Conforms to requirements of BS EN 15102, BS EN 259 and WA – Quality Standard W-101.

Stain/Chemical Resistance:

Pass ASTM D-1308-1987 Federal Spot Test. Resistant to tempo rary stain ing of oils, fats, mild acids and alkalis.

Quality Assurance:

Our management systems and production procedures comply with ISO 9001: 2015, the internationally recognised Quality Standard.

Availability:

Every product stocked in depth. 5.00pm deadline for next day delivery. (UK only)

Origin:

Designed, coloured, manufactured and stocked in the UK.

Warranty:

Newmor offers a five year warranty against manufacturing defects. Full details available on application.

Samples:

Larger samples are readily available on request.

Maintenance:

Fully washable and in most cases products can be scrubbed repeatedly to remove any marks without damaging the product itself. Also able to withstand the use of chlorine releasing agent solutions.



This product contains at least 20% recycled material

